

TECHNICAL DATA SHEET

CROMASEAL

Issue 6 – October 2015

Description:

Cromaseal is a high performance, cold applied waterproof membrane, manufactured from tough cross-orientated HDPE film to a layer of rubber modified bitumen adhesive.

The advanced backing film gives improved technical performance on tear strength and tensile strength, puncture resistance and dimensional stability. It also offers good conformability for site application.

After installation the membrane should be covered as soon as possible with a cementitious screed or similar protective layer.

Benefits:

- Excellent overlap integrity due to bitumen to bitumen joint using zip strip.
- Factory controlled thickness
- Rapid and easy cold application
- Flexible and accommodating giving excellent bond to substrate
- Non-hazardous and resistant to dilute acids and alkalis
- High performance protection against surface and ground water and soluble salts such as sulphates and chlorides.
- Capable of resisting a 6 metre head of water when fully supported

Uses:

For General Waterproofing

1. Internal and External tanking of underground structures
2. Reservoirs
3. Car Park and Roof Decks
4. Subway, Lift Shafts and Retaining Walls

Product Details:

Roll:-

Recommended Minimum Overlap:-

Length:	19.05m	Adjacent Rolls	50mm
Width:	1.05m	Roll Ends	100mm
Area:	20m ²		
Weight:	34kg		

Technical Property	Unit	Test Method	Typical Result
Backing Film	Mm	ASTM D1000	0.10
Total Membrane Thickness	Mm	ASTM D1000	1.50
Tensile Strength – Membrane	N/mm	ASTM D638	4.2 Length 4.8 width
Elongation – Membrane - Compound	%	ASTM D638	210 Length 160 Width >1300

Technical Property	Unit	Test Method	Typical Result
Tear Strength	N	ASTM D1004	34 Length 31 Width
Puncture Resistance	N	ASTM E154	220
Adhesion – to Self - to Primed Concrete*	N/mm	ASTM D1000	4.0 3.0
Water Vapour Transmission	g/m ² /24hr	ASTM E96	0.3
Vapour Resistance	MNs/g	BS 3177	600
Water Penetration/Joint	%	MOAT 27 (5.1.4)	NIL
Dimensional Stability	%80°C	MOAT 27 (5.1.6)	-0.1 Length -0.2 Width
Temperature Range: Application Storage	°C	Tropical +15 to +45 Below 45	Temperate +5 to +35 Below 35
Approx. Coverage*	8m ² /1		
Primer	Cromar Bituminous Primer		

*Results vary greatly depending on the porosity of the concrete. (Note – High porosity concrete can give significantly lower results)

Storage:

The membrane rolls must be stacked on end and stored in dry, well-ventilated buildings, out of direct sunlight or other major sources of heat. Storage conditions should be adjusted before application to bring the temperature of the rolls to within the relevant specified application range.

Health & Safety:

Cromar's Bituminous Primer gives off flammable vapour and should be stored in accordance with local hazard requirements.

Health & Safety:

Please refer to health & safety data sheet on Cromaseal.

Further Information:

In the event of further queries or problems concerning the use of this product, please contact the address below, or e-mail info@cromar.uk.com.

All products should be sold in accordance with the manufacturer's instructions. The manufacturer cannot be held responsible where conditions of use are beyond our control. Cromar Building Products Limited products are available for sale in accordance with Cromar Building Products Limited standard conditions of sale, which is available upon request. Whilst any information contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendations, agents, or distributors, as the conditions of use and any labour involved are beyond our control. Our warranty is therefore limited to the quality of supplied product.



Units 3,4,5 Northside Industrial Estate, Whitley Bridge, North Yorkshire DN14 OGH

www.cromar.uk.com

Tel: 01977 663133 Fax: 01977 662186 E-mail: info@cromar.uk.com