

TECHNICAL DATA SHEET

ELASTATEX

Reinforcement Membrane

DESCRIPTION:

Non-woven, needle-punched reinforcement membrane.

AREAS OF USE:

Reinforcement of upstands, joints cracks and gaps in flat roofs in conjunction with Elasta-thane 25 system.

DIRECTIONS FOR USE:

Elastatex membrane is applied *during* the application of the Elasta-thane 25 liquid. Apply approx. half of the liquid to the target surface, and bed down the Elastatex membrane, then apply the remainder of the liquid on top, wetting out thoroughly by roller & ensuring there are no air bubbles or wrinkles. Overlap strips by approx. 100mm.

SURFACE PREPARATIONS AND FINISHING

Surface preparation and priming must be exactly as for Elastathane 25.

PACKAGING:

1m wide by 25m and 50m rolls.

COLOUR(S)

White

SHELF LIFE:

12 months from production date. Store in unopened, original packaging between +5°C and +25°C in cool, dry conditions.

ADDITIONAL INFORMATION:

Parameter	Nominal value	Standard
Density	85 g/m ²	
Thickness	0.55mm	EN/ISO 9073-2
Breaking strength - MD	220 N	DIN 53858
Breaking strength - CD	265 N	DIN 53858
Elongation at 90N - MD	18 %	DIN 53858
Elongation at 90N - CD	23 %	DIN 53858
Tear resistance - MD	105 N	EN/ISO 9073-4
Tear resistance - CD	85 N	EN/ISO 9073-4
Bending length - MD	5 N	EN/ISO 9073-7
Bending length - CD	5 N	EN/ISO 9073-7

Health & Safety

Safety data sheet (MSDS) must be read and understood before use of product. These are available on request.

Further Information:

In the event of further queries or problems concerning the use of this product, please contact the address below, e-mail info@cromar.uk.com.

All products should be sold in accordance with the manufacturer's instructions. The manufacturer cannot be held responsible where conditions of use are beyond our control. Cromar Building Products Limited products' are available for sale in accordance with Cromar Building Products Limited standard conditions of sale, which is available upon request. Whilst any information contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendations, agents, or distributors, as the conditions of use and any labour involved are beyond our control. Our warranty is therefore limited to the quality of supplied product.



Units 3,4,5 Northside Industrial Estate, Whitley Bridge, North Yorkshire DN14 OGH

www.cromar.uk.com

Tel: 01977 663133 Fax: 01977 662186 E-mail: info@cromar.uk.com