

# TECHNICAL DATA SHEET

## Contractor – TOPCOAT

Issue 2 – April 2020

### Description:

Cromar Contractor Topcoat is a dark grey, pre-pigmented, isophthalic acid based, filled fire-retardant roofing top-coat.

### Approvals:

Conforms to BS476 Part 3:2004, FAB classification.

When applied at a wet film thickness of 500 – 600 microns and fabricated with a single ply of 450 grams per square metre of emulsion bound chopped strand mat, consolidated with the optimum quantity of an orthophthalic acid based general purpose laminating resin onto 18 mm OSB3 grade board.

Contact our Technical Service Department for specific recommendations.

### Product use:

CROMAR Contractor Topcoat is recommended for use in flat roofing applications where regulations specify a fire-retardant system.

### Characteristics:

CROMAR Contractor Topcoat is designed for roller application which exhibits good levelling characteristics and sag resistance on inclined surfaces. The cured top-coat is tack-free and water-tight with excellent water and weather resistance providing a maintenance-free surface.

### Application:

CROMAR Contractor TOPCOAT is designed for use at ambient temperatures between 18°C and 25°C, and requires the addition of 2% medium activity MEKP catalyst to achieve an efficient cure. For optimum performance the top-coat should be applied to a dry, dust-free surface and built up to film thickness of 500 - 600 microns to achieve the desired fire retardant characteristics in the finished structure.

Before use, the temperature of the top-coat should be 18 – 25oC.

For application at lower ambient temperatures a high activity MEKP catalyst can be used at an addition level of 2%.

### Liquid gel coat properties:

Appearance	Dark grey liquid
Liquid properties	Thixotropic
Gel time @ 25°C	<15 minutes
2% medium activity MEKP	

**Health & Safety:**

Please refer to the Material Safety Data Sheet on Cromar Contractor – Topcoat.

Always read and understand the Material Safety Data Sheet before working with this product.

Directly mixing any organic peroxide with a metal soap, amine or other polymerization accelerator or promoter will result in violent decomposition.

**Further Information:**

In the event of further queries or problems concerning the use of this product, please contact the address below, e-mail [info@cromar.uk.com](mailto:info@cromar.uk.com) or telephone our Technical Line on 01977 663 133 Option 4:

All products should be sold in accordance with the manufacturer's instructions. The manufacturer cannot be held responsible where conditions of use are beyond our control. Cromar Building Products Limited products' are available for sale in accordance with Cromar Building Products Limited standard conditions of sale, which is available upon request. Whilst any information contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendations, agents, or distributors, as the conditions of use and any labour involved are beyond our control. Our warranty is therefore limited to the quality of supplied product.



Units 3,4,5 Northside Industrial Estate, Whitley Bridge, North Yorkshire DN14 OGH

[www.cromar.uk.com](http://www.cromar.uk.com)

Tel: 01977 663133 Fax: 01977 662186 E-mail: [info@cromar.uk.com](mailto:info@cromar.uk.com)