

TECHNICAL DATASHEET

Fire Rated Acoustic Sealant

Description & Uses

Cromar Alpha Chem Acoustic Fire Rated Sealant is a high quality, one part, flexible 4 hour fire rated sealant used for sealing linear joints and gaps in walls and floors to maintain the acoustic, air and fire resistant performance of a compartment.

It also has excellent sound reduction properties, offering a reduction of 63dB and fire tested in accordance with EN1366-4 in joints up to 50mm.

Key Features

- Offers up to 63dB sound reduction
- Tested in accordance with EN1366-4
- Classified in accordance with EN13501-2
- For use in joints up to 50mm
- Easy tooling
- No slump
- Good adhesion to most construction substrates
- No priming required with most construction substrates
- Halogen free
- Paintable when fully cured

Ideal for

- For sealing connecting, expansion and perimeter joints
- To form an acoustic barrier when sealing joints in plasterboard/flexible walls, ridged floors, metal studwork and blockwork
- For sealing joints to maintain compartmentation within a building, including air permeability and acoustics

Directions

- Fill any gaps or voids with a suitable backing tape or rod.
- For good adhesive to surfaces, ensure all surfaces are clean, sound, dry and free from dust, grease or other contaminants. Ensure surfaces have not been pre-treated with any primers or coatings.
- Ensure the site conditions are within the application specification.
- Apply sealant cartridge with a sealant gun, or foil with a foil applicator gun, and tool down using a spatula wetted with water to produce a professional finish.
- Tools should be cleaned immediately after use.
- Tack free within 30 minutes, curing 2mm per 24 hours dependent on conditions.
- It is the user's responsibility to dispose of all packaging correctly.



Storage

Store in cool, dry conditions between +5°C and +25°C, off the floor.

Shelf Life

24 months when stored in original, unopened packaging.

Limitations

- It is the user's responsibility to ensure suitability for use.
- **Please read the label before use as this contains essential safety information, Product Safety Sheet available on request.**

Technical Data

SG	1.6
Skin Formation Time Approx. (mins)	30
Curing Rate mm / 1 day	2
Application Temperature	+5 to +30°C
Shore A Hardness Approx. (ISO 7619-1)	8.15
Elongation at Break (%)	100
Joint Movement Accommodation (%)	7.5
Operating Temperature	-5 to +40°C
Modulus at 100% Elongation Approx. (MPa)	0.98

Further Information:

In the event of further queries or problems concerning the use of this product, please contact the address below, e-mail info@cromar.uk.com.

All products should be sold in accordance with the manufacturer's instructions. The manufacturer cannot be held responsible where conditions of use are beyond our control. Cromar Building Products Limited products' are available for sale in accordance with Cromar Building Products Limited standard conditions of sale, which is available upon request. Whilst any information contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendations, agents, or distributors, as the conditions of use and any labour involved are beyond our control. Our warranty is therefore limited to the quality of supplied product.