

## TECHNICAL DATA SHEET STABILISING SOLUTION

#### Issue 5 – November 2015

#### **Description:** Stabilising Solution is a treatment for friable and chalking surfaces.

# **Uses:** Stabilising Solution is a low viscosity solution, which when applied to dusting, chalking or friable surfaces, will consolidate then to give a suitable base for redecoration.

**Directions:** All friable and loose material must be removed by a stiff bristled brush and scraping. Any fungal growth should be treated with Moss & Mould Remover; applied liberally by brush or low pressure pneumatic spray. Allow 24 hours and remove all debris, before applying Stabilising Solution. Normally only one coat of Stabilising Solution is necessary and this must be brushed well into the surface as it is extremely important that the solution is completely absorbed, and that a surplus of the material does not lie on the surface. Treated surfaces should be allowed to dry for at least 16 hours before recoating.

Container Sizes: 2.5, 5 and 25 litres

- **Coverage:** On smooth surfaces 25-30m<sup>2</sup> per 5 litres. On rough textured surfaces or those that have a high suction, the coverage will be much reduced.
- **Drying Time:** 4 8 hours, depending on atmospheric conditions. Allow 16 hours before recoating with masonry paints.

Health & Safety: Please refer to health and safety data sheet on Stabilising Solution.

### **Further Information:**

In the event of further queries or problems concerning the use of this product, please contact the address below, or e-mail <u>info@cromar.uk.com</u>.

All products should be sold in accordance with the manufacturer's instructions. The manufacturer cannot be held responsible where conditions of use are beyond our control. Cromar Building Products Limited products' are available for sale in accordance with Cromar Building Products Limited standard conditions of sale, which is available upon request. Whilst any information contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendations, agents, or distributors, as the conditions of use and any labour involved are beyond our control. Our warranty is therefore limited to the quality of supplied product.



Units 3,4,5 Northside Industrial Estate, Whitley Bridge, North Yorkshire DN14 OGH www.cromar.uk.com Tel: 01977 663133 Fax: 01977 662186 E-mail: info@cromar.uk.com